

تجهيزات بتن خاورميانه

MECONACC
Middle East Concrete Accessories



Société Nouvelle du Littoral

Siège Social & Usine : Z.A. – BP 9 – 11370 LEUCATE (France)
Tél. : 33 (0) 4 68 40 14 05 – Fax : 33 (0) 4 68 40 92 72

www.beton-co.ir Email: info@beton-co.ir



1- CHARACTERISTICS

The sand is natural siliceous sand having a water content lower than 0.1 %. The constituent grains are uncrushed and rounded form. They have a silica content higher than 98 %.

It is packadeg in polyéthylène bag of 1000 ± 10 g.

Deliveries are made in boxes of 20 bags weighing 20.5 kg and in pallets of 36 to 45 boxes with gross weight of 750 to 935 kg suitably protected by a polyethylene cover (land transport) or reinforced boxes (shipping).

2- CONTROLS

Grading requirement of this sand is fixed by NF T 66-061. It corresponds to 0.1/0.63. The sand average grading is :

Square mesh size in (mm)	Cumulative passing (%)		
	Average grading	SNL spécifications	NF T 66061
1,25	100	100	
0,63	100	90 à 100	maxi
0,5	98,8		
0,315	48,7		
0,2	9		
0,1	1	0 à 10	mini
0,08	0,4	0 à 1	

Grading is controled by 200 kg batch of sand. Water content is measured by 1000 kg batch. Controls are carried out by SNL Laboratory.



S.N.L. fondée en 1910 – SAS capital 250 000 € - NIF FR 93 976 750 257 – SIRET 976 750 257 00025 APE 0812Z
Certifiée pour la PREPARATION DU SABLE NORMALISE CEN POUR LA DETERMINATION DES RESISTANCES MECANQUES DES CIMENTS

